



# ONE CAN OC64 - EGGSHELL

**A quick-drying, low-odour, water-thinned primer/finish coat, with excellent adhesion, stain blocking and anticorrosive properties.**

## Recommended Areas of Use

For use as a quick-drying, adhesion-promoting, stain-blocking and anti-corrosive coating on ferrous metals, non-ferrous metals, common plastics (e.g. melamine and uPVC), ceramic tiles, glass, wood and existing painted surfaces. Offers a hard-wearing, flexible coating with weather and light resistance, ideal for use over existing cladding coatings (coil, plastisol and powder coatings) with minimal preparation.

## Certificates & Approvals

Manufactured under the auspices of ISO 9001:2015 quality & ISO 14001:2015 environmental management systems. 2004/42/EC EU limit value for this product (Annex IIA/i. wb): 140g/l (2010). This product contains max 30 g/l VOC.

## Properties

<b>Gloss</b>	Eggshell (approx. 25%)	<b>Surface dry</b>	30 Minutes
<b>Theoretical Coverage</b>	12m <sup>2</sup> /L/coat	<b>Minimum over coating time</b>	1 hour minimum*
<b>Recommended number of coats</b>	2 coats minimum as a finish 3 coats for stain locking	<b>Maximum over coating time</b>	Unlimited
<b>Density</b>	1.24 kg/L	<b>Minimum application conditions</b>	10°C or above for application (minimum of 3°C above dew point)
<b>Volume solids</b>	41%	<b>Full Cure</b>	7 days
<b>Flash point (Abel closed cup)</b>	Non-Flammable	<b>Shelf life</b>	2 years minimum in original unopened containers.
<b>VOC</b>	30 g/L	<b>Colour range</b>	White & Black standard colours, RAL, British Standard, NCS.
<b>Thinner / Cleaning</b>	Water		
<b>Recommended wet film thickness</b>	75-100 microns/coat	<b>Recommended dry film thickness</b>	35 microns/coat

## Suitable Surfaces

Suitable for use over most properly cleaned and prepared interior and exterior commercial wood, plastic and metals. Compatibility with existing coatings should be confirmed by preparing and painting a test patch. Anticorrosive for application to ferrous and non-ferrous metals which have been fully prepared. Seals most stains in the primer coat including water, nicotine, hardwood resin bleed, asphalt, and many more.

## Application Information

\*Drying times will be prolonged at lower temperatures and over application.

All surfaces must be dry and dust free before coating. Application should always conform with the codes of practice described in BS 6150 and BS 5493. Film may take upto 7 days to fully cure, depending on number of coats, film thickness and local conditions. During this period, if rain/moisture is introduced to the coating watermarks may be visible. This will be more apparent in darker shades.

**Brush and Roller** - Supplied ready for use. Thin with 5-15% water if required.

**Conventional Air Spraying** - Thin with 5-15% water as required. Tip size - 2.0mm. Tip pressure - 60psi (0.4MPa) approximately. (Guidelines Only).

**Airless Spraying** - Thin with 5-15% water as required. Tip size - 19 thou (0.48mm) approximately. Tip pressure - 2100 psi (15MPa) approximately. (Guidelines Only).

## Cleaning

Equipment should be cleaned immediately after use with water.

## Specifications

### Surface Preparation

Loose and non-adhered coatings should be removed. Cleaning using Bradite Industrial Degreaser TD39 or methylated spirit is recommended to remove oils, grease and other contamination.

Intact areas of existing coatings should, ideally, be roughened by manual or mechanical sanding. Feather back any exposed areas to a sound coating edge. Cracks and pits should be filled using a suitable filler before painting. Substrate should be dust free and completely dry before coating.

**Stain locking:** Encapsulates stains in the primer coat, application of second coat will be required to hide, and in extreme cases a third coat may be required. One Can should be allowed to hard dry prior to overcoating. This will take at least one hour, over application may result in longer drying times

**Aluminum, stainless steel, galvanised steel, copper and other metals:** Cleaned and degreased with methylated spirit, and lightly abraded if possible. White salts on weathered galvanising must be removed during cleaning and degreasing. Light surface rusting should be treated with Bradite Rust Convertor RC46. Heavy rusting to be removed to clean metallic finish (SIS-St 3).

**New Wood:** Ensure moisture content of the timber is below 15% before commencing application. Damp wood should never be painted as this may give rise to blistering, flaking, cracking and premature coating failure. Knots to be wiped using methylated spirit, for heavy or active knots spot prime with aluminium wood primer.

**Hard Woods:** Wipe with methylated spirit to remove excess resin, changing the face of the cloth regularly. Lightly abrade.

**Green oak:** Should not be painted unless it has been weathered for at least 6 months.

**Exterior cladding, Powder coated, Varnish and Existing paint finish:** Remove all loose and flaking paintwork. Degrease using Bradite Industrial Degreaser TD39, followed by clean water rinse. Rub down thoroughly with a medium grade sandpaper to provide a key and a defect free smooth surface, "feathering in" areas where paint has been removed.

**UPVC, Formica, Melamine and Plastics:** For long term performance, degrease using Bradite Industrial Degreaser TD39 or methylated spirit & lightly abrade surfaces.

**New plaster walls:** For plaster skim, allow at least four weeks for the plaster to thoroughly dry. Apply a primer coat by thinning the paint with a 5 to 25% (v/v) addition of clean water, depending upon the porosity of the substrate. Cut in by brushing at the same dilution recommendation as for priming, to promote flow and sealing of the substrate.

For new, fully plastered walls, allow at least six months for the plaster to thoroughly dry before painting.

This product is not recommended for painting lime or other natural plasters.

**Masonry, brick, concrete:** Clean, dry and free of contamination, existing coatings to be sound and well adhered. Any loose flaking material should be removed and sanded back to a sound, well-feathered edge. New concrete or masonry to be fully cured. Mould or mildew to be removed and area treated with good quality fungicidal wash following manufacturer's instructions.

## Painting System

1st coat	Bradite ONE CAN OC64
2nd coat	Bradite ONE CAN OC64
3rd coat	Bradite ONE CAN OC64 [If required]

## Summary Safety Information

Always refer to the Health and Safety sheet for the product before use, and observe the warning phrases on the label. In general, avoid inhalation of spray mist and skin contact by the use of masks, gloves and other personal protection. Eyes should be copiously washed with water or proprietary wash, and medical attention obtained. Skin should be thoroughly washed using a cleanser and soap and water.

**Disclaimer** - The information on this data sheet is correct to the best of our knowledge and experience. Bradite reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.